

Product Data Sheet

Sarlink® 6135N

Typical properties*	Test method	S.I.		U.S.	
		Typical value	Units	Typical value	Units
Density	ISO 1183	888	kg/m ³	888	kg/m ³
Hardness Shore (5 sec delay)	ISO 868				
Extruded sample		32A		32A	
Injection molded sample		36A		36A	
Tensile Properties	ISO 37				
<u>Flow direction</u>					
Tensile strength at break		2.3	MPa	334	Psi
Modulus at 100% elongation		1.1	MPa	160	Psi
Elongation at break		374	%	374	%
<u>Cross direction</u>					
Tensile strength at break		2.7	MPa	392	Psi
Modulus at 100% elongation		0.8	MPa	116	Psi
Elongation at break		555	%	555	%
Tear Strength	ISO 34B				
<u>Cross direction</u>					
Unnicked angle		10.5	kN/m	60	Pli
Compression set	ISO 815				
22h/23°C		23	%	23	%
22h/70°C		30	%	30	%
70h/125°C		43	%	43	%
Rheology	ISO 11443				
<u>Apparent Shear Viscosity</u>	Capillary				
@ 206 1/s, 200°C		195	Pa.s	195	Pa.s

* Tests are conducted on injection-molded plaques unless indicated otherwise.

All information supplied by or on behalf of DSM in relation to its products, whether in nature of data, recommendations or otherwise, is supported by research and believed reliable, but DSM assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or products, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to DSM for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.