

Product Data Sheet

Sarlink® 5725B4

Typical properties*	Test method	S.I.		U.S.	
		Typical value	Units	Typical value	Units
Density	ISO 1183	930	kg/m ³	930	kg/m ³
Hardness Shore (5 sec delay)	ISO 868	23A		23A	
Extruded sample		26A		26A	
Injection molded sample					
Tensile Properties	ISO 37				
<u>Flow direction</u>					
Tensile strength at break		1.5	MPa	218	Psi
Modulus at 100% elongation		1.1	MPa	160	Psi
Elongation at break		200	%	200	%
<u>Cross direction</u>					
Tensile strength at break		2.5	MPa	363	Psi
Modulus at 100% elongation		0.5	MPa	73	Psi
Elongation at break		510	%	510	%
Tear Strength	ISO 34B	9	kN/m	51	Pli
<u>Cross direction</u>					
Unnicked angle					
Compression set	ISO 815				
22h/23°C		10	%	10	%
22h/70°C		20	%	20	%
70h/125°C		51	%	51	%
Hot air aging	ISO 188				
<u>168h/150°C, Cross Direction</u>					
Change in hardness		-3	points	-3	points
Retention tensile strength at break		96	%	96	%
Retention modulus at 100% elongation		93	%	93	%
Retention elongation at break		82	%	82	%
<u>1000h/135°C, Cross Direction</u>					
Change in hardness		-1	points	-1	points
Retention tensile strength at break		96	%	96	%
Retention modulus at 100% elongation		93	%	93	%
Retention elongation at break		76	%	76	%
Volume swell	ISO 1817	71	%	71	%
70h/125°C in IRM 903 oil					
Rheology	ISO 11443	140	Pa.s	140	Pa.s
<u>Apparent Shear Viscosity</u>					
@ 206 1/s, 200°C	Capillary				

* Tests are conducted on injection-molded plaques unless indicated otherwise.

All information supplied by or on behalf of DSM in relation to its products, whether in nature of data, recommendations or otherwise, is supported by research and believed reliable, but DSM assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or products, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to DSM for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.