

Product Data Sheet

Sarlink® 5740DB4

Typical properties*	Test method	S.I.		U.S.	
		Typical value	Units	Typical value	Units
Density	ISO 1183	960	kg/m ³	960	kg/m ³
Hardness Shore (5 sec delay) Extruded sample Injection molded sample	ISO 868	38D 40D		38D 40D	
Tensile Properties <u>Flow direction</u> Tensile strength at break Modulus at 100% elongation Elongation at break <u>Cross direction</u> Tensile strength at break Modulus at 100% elongation Elongation at break	ISO 37	18.0 13.3 490 19.0 9.0 640	MPa MPa % MPa MPa %	2611 1929 490 2756 1305 640	Psi Psi % Psi Psi %
Tear Strength <u>Cross direction</u> Unnicked angle	ISO 34B	88	kN/m	502	Pli
Compression set 22h/23°C 22h/70°C 70h/125°C	ISO 815	46 58 80	% % %	46 58 80	% % %
Hot air aging <u>168h/150°C, Cross Direction</u> Change in hardness Retention tensile strength at break Retention modulus at 100% elongation Retention elongation at break <u>1000h/135°C, Cross Direction</u> Change in hardness Retention tensile strength at break Retention modulus at 100% elongation Retention elongation at break	ISO 188	3 78 105 75 3 80 109 75	points % % % points % % %	3 78 105 75 3 80 109 75	points % % % points % % %
Volume swell 70h/125°C in IRM 903 oil	ISO 1817	47	%	47	%
Rheology <u>Apparent Shear Viscosity</u> @ 206 1/s, 200°C	ISO 11443 Capillary	400	Pa.s	400	Pa.s

* Tests are conducted on injection-molded plaques unless indicated otherwise.

All information supplied by or on behalf of DSM in relation to its products, whether in nature of data, recommendations or otherwise, is supported by research and believed reliable, but DSM assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or products, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to DSM for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other property by reason of the application, processing or use of the aforementioned information or products by the buyer.