

Product Data Sheet

Sarlink® 4149D

Typical properties*	Test method	S.I.		U.S.	
		Typical value	Units	Typical value	Units
Density	ISO 1183	940	kg/m ³	940	kg/m ³
Hardness Shore (5 sec delay)	ISO 868	47D		47D	
Extruded sample		51D		51D	
Injection molded sample					
Tensile Properties	ISO 37				
<u>Flow direction</u>					
Tensile strength at break		21.6	MPa	3133	Psi
Modulus at 100% elongation		18.0	MPa	2611	Psi
Elongation at break		420	%	420	%
<u>Cross direction</u>					
Tensile strength at break		23.1	MPa	3350	Psi
Modulus at 100% elongation		13.0	MPa	1885	Psi
Elongation at break		740	%	740	%
Tear Strength	ISO 34B				
<u>Cross direction</u>					
Unnicked angle		141	kN/m	805	Pli
Compression set	ISO 815				
22h/23°C		55	%	55	%
22h/70°C		64	%	64	%
70h/125°C		85	%	85	%
Hot air aging	ISO 188				
<u>168h/150°C, Cross Direction</u>					
Change in hardness		2	points	2	points
Retention tensile strength at break		85	%	85	%
Retention modulus at 100% elongation		115	%	115	%
Retention elongation at break		80	%	80	%
<u>1000h/135°C, Cross Direction</u>					
Change in hardness		2	points	2	points
Retention tensile strength at break		92	%	92	%
Retention modulus at 100% elongation		125	%	125	%
Retention elongation at break		80	%	80	%
Volume swell	ISO 1817				
70h/125°C in IRM 903 oil		38	%	38	%
Rheology	ISO 11443				
<u>Apparent Shear Viscosity</u>					
@ 206 1/s, 200°C	Capillary	440	Pa.s	440	Pa.s

* Tests are conducted on injection-molded plaques unless indicated otherwise.

The information and suggestions contained in this bulletin are, to the best of our knowledge, accurate and reliable but no guarantee of their accuracy is made. All products are sold upon condition that purchasers shall make their own tests to determine the suitability of such products for their particular purposes and uses and purchasers assume all risks and liability for the results of use of the products, including use in accordance with seller's suggestions. Nothing in this bulletin constitutes permission or a recommendation to practice or use any invention covered by any patent owned by this company or by others. There is no warranty of merchantability and there are no other warranties for the products described.

© SARLINK® is a registered trademark of Teknor Apex Company
v. 04.2011